

® = registered trademark of BASF SE

Irganox[®] PS 800

Thiosynergist Heat Stabilizer

Characterization

Irganox PS 800 is a dialkyl ester of thiodipropionic acid. It is used as a heat stabilizer in combination with a phenolic antioxidant.


Chemical name

Didodecyl-3,3'-thiodipropionate

CAS number

123-28-4

Chemical formula



Molecular weight

515 g/mol

Applications

- Polymer materials requiring long-term thermal stability
- Polyethylene power cables
- XLPE power cables
- HDPE pipe
- Polypropylene
- Polyolefin under-hood automotive applications
- Styrene homo- and copolymers
- Adhesives

Features/benefits

Irganox PS 800 used in combination with a primary phenolic antioxidant provides general purpose heat stabilization. With the highest compatibility and lowest melting point of common thiosynergists, it is most easily incorporated into the final product. It is most widely used in combination with Irganox 1035 for peroxide cross-linked power cables.

Product forms

Irganox PS 800 FL white crystalline flakes

Guidelines for use

In general Irganox PS 800 can be used to improve the long-term heat stability of polymers at recommended levels of 0.05 % – 1 %. In peroxide cross-linked power cables, 0.02 % – 0.03 % Irganox PS 800 in combination with 0.02 % – 0.03 % Irganox 1035.

Physical Properties

Melting range	39–41 °C
Flashpoint	219 °C
Density (25 °C)	1.04 g/ml
Vapor pressure (20 °C)	6.6 E-6 Pa

Bulk density FL	400–450 g/l
--------------------	-------------

Solubility (20 °C)	g/100 g solution
Acetone	37
Chloroform	> 50
Ethanol	2.2
Ethyl acetate	33
n-Hexane	20
Water	0.001

Health & Safety

Irganox PS 800 exhibits a very low order of oral toxicity and does not present any abnormal problems in its handling or general use.

Detailed information on handling and any precautions to be observed in the use of the product(s) described in this leaflet can be found in our relevant health and safety information sheet.

Note

The descriptions, designs, data and information contained herein are presented in good faith, and are based on BASF's current knowledge and experience. They are provided for guidance only, and do not constitute the agreed contractual quality of the product or a part of BASF's terms and conditions of sale. Because many factors may affect processing or application/use of the product, BASF recommends that the reader carry out its own investigations and tests to determine the suitability of a product for its particular purpose prior to use. It is the responsibility of the recipient of product to ensure that any proprietary rights and existing laws and legislation are observed. No warranties of any kind, either expressed or implied, including, but not limited to, warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth herein, or that the products, descriptions, designs, data or information may be used without infringing the intellectual property rights of others. Any descriptions, designs, data and information given in this publication may change without prior information. The descriptions, designs, data and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

September 2010