

® = registered trademark of BASF SE

# Irgastab® PUR 55

## Anti-scorch package for polyols

### Characterization

Irgastab PUR 55 is a BHT free liquid heat stabilizer blend for polyether- and polyester-based flexible pur foams.

### Applications

Irgastab PUR 55 is particularly suitable for the stabilization of polyols used for the manufacture of flexible foams. Irgastab PUR 55 can also be added with additional antioxidants and/or co-stabilizers (e. g. phosphites) and/or light stabilizers (e. g. HALS, UV absorbers).

### Features/benefits

Irgastab PUR 55 exhibits good resistance to scorch, fogging, textile staining. Irgastab PUR 55 is a pourable liquid allowing dust free handling, automatic dosage and shortening of mixing time. It allows gaining productivity in reducing weighing and metering to one single operation.

### Product forms

Irgastab PUR 55                      clear, yellow liquid product

### Guidelines for use

In slabstock polyol applications, the concentration of Irgastab PUR 55 ranges between 0.4 % and 0.7 % depending on the degree of stabilization desired. Additional performance data in polyols are available upon request.

### Physical properties

Boiling point	> 200 °C
Flashpoint	> 150 °C
Viscosity (40 °C)	> 100 mm <sup>2</sup> /s
Relative density (20 °C)	0.95 – 1.00 g/ml
Vapor pressure (20 °C)	< 0.1 Pa

### Health & Safety

Irgastab PUR 55 exhibits a very low order of oral toxicity and does not present any abnormal problems in its handling or general use.

Detailed information on handling and any precautions to be observed in the use of the product(s) described in this leaflet can be found in our relevant health and safety information sheet.

**Note**

The descriptions, designs, data and information contained herein are presented in good faith, and are based on BASF's current knowledge and experience. They are provided for guidance only, and do not constitute the agreed contractual quality of the product or a part of BASF's terms and conditions of sale. Because many factors may affect processing or application/use of the product, BASF recommends that the reader carry out its own investigations and tests to determine the suitability of a product for its particular purpose prior to use. It is the responsibility of the recipient of product to ensure that any proprietary rights and existing laws and legislation are observed. No warranties of any kind, either expressed or implied, including, but not limited to, warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth herein, or that the products, descriptions, designs, data or information may be used without infringing the intellectual property rights of others. Any descriptions, designs, data and information given in this publication may change without prior information. The descriptions, designs, data and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

September 2010